



VINCIBRIGHT
FULLY COATED WHITE LINED CHIPBOARD
WITH MANILLA BACK
GT

TECHNICAL SPECIFICATION

JULY 2019

SUBSTANCE	CALIPER	BULK	STIFFNESS			
			TABER 15°		L&W 5° (*)	
			MD	CD	MD	CD
ISO 536	ISO 534	ISO 534	ISO 2493		DIN 53121	
g/m²	mm	cm³/g	mN.m	mN.m	mN.m	mN.m
(270)	0.359	1.33	9.1	3.7	17.3	6.9
290	0.384	1.32	11.2	4.8	21.3	9.1
320	0.425	1.33	15.4	6.7	29.3	12.8
350	0.465	1.33	19.7	9.0	37.5	17.1
385	0.505	1.31	24.6	11.4	46.7	21.7
400	0.525	1.31	27.7	13.0	52.7	24.8
(425)	0.556	1.31	30.9	14.4	58.7	27.3
450	0.590	1.31	36.2	17.0	68.8	32.3
(480)	0.630	1.31	41.0	18.7	77.8	35.5
(500)	0.655	1.31	44.1	20.0	83.8	37.9

() NON STANDARD GRAMMAGE, AVAILABLE ON SPECIAL REQUEST ONLY.
 (*) TABER FIGURES ARE GUARANTEED; L&W FIGURES ARE CALCULATED.

BRIGHTNESS (AT PRODUCTION)		
TOP	82% +/- 2	ISO 2470-2
BACK	55% +/- 2	ISO 2470-2

TOLERANCES - SAMPLING ISO 186		
SUBSTANCE	+/- 2%	average of order
CALIPER	+/- 5%	for single determinations (95% of values)
STIFFNESS	- 15%	for single determinations (95% of values)
TEST CONDITIONS	T: 23° C +/- 1	RH: 50% +/- 2

CERTIFICATIONS: ISO 9001 / ISO 14001 / ISO 50001 / OHSAS 18001
 FSC® C081817 - PEFC™ SA-PEFC/COC-005109: CERTIFIED BOARD IS AVAILABLE ON REQUEST

